

## REPORT DOCUMENTATION PAGE

Form Approved  
OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE August 5, 1997		3. REPORT TYPE AND DATES COVERED Final Technical (4/1/94 to 8/31/97)	
4. TITLE AND SUBTITLE Synthesis and Processing of New Second Order Nonlinear Optical Materials				5. FUNDING NUMBERS F49620-94-1-0201  2303/CS 61102F	
6. AUTHOR(S)  Larry R. Dalton					
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)  University of Southern California Department of Chemistry Loker Hydrocarbon Research Institute Los Angeles, CA 90089-1661				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES)  Dr. Charles Y.-C. Lee Air Force Office of Scientific Research Bolling Air Force Base, D.C. 20332-6448  NL				10. SPONSORING / MONITORING AGENCY REPORT NUMBER	
11. SUPPLEMENTARY NOTES					
12a. DISTRIBUTION / AVAILABILITY STATEMENT  Approved for Public Release : Distribution Unlimited				12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words)  Fundamental studies have been conducted on the factors which determined chromophore hyperpolarizability to optical loss ratio and which determined chromophore interaction leading to attenuation of electric field poling-induced electro-optical activity. These studies have lead to a new generation of electro-optic materials exceeding for the first time the performance of inorganic electro-optic materials. Lattice hardening chemistry used to lock-in poling-induced electro-optic activity has been systematically investigated. Fundamental studies of poling-induced optical loss have been conducted. A new technique for processing polymer buried channel waveguides, multi-color photolithography, has been introduced.					
14. SUBJECT TERMS Electro-optic materials, London forces, electric field poling, multi-color photolithography, buried channel optical waveguides, high bandwidth modulators, lattice hardening, integrating disparate				15. NUMBER OF PAGES 18	
				16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT  U		18. SECURITY CLASSIFICATION OF THIS PAGE  U		19. SECURITY CLASSIFICATION OF ABSTRACT  U	
				20. LIMITATION OF ABSTRACT  U	

SYNTHESIS AND PROCESSING OF NEW SECOND ORDER NONLINEAR OPTICAL  
MATERIALS  
F49620-94-1-0201

Final Progress Report Submitted to


DR. CHARLES Y-C. LEE  
DIRECTORATE OF CHEMISTRY AND MATERIALS SCIENCE  
AIR FORCE OFFICE OF SCIENTIFIC RESEARCH  
BOLLING AFB, WASHINGTON, D.C. 20332-6448

by

LARRY R. DALTON  
PROFESSOR OF CHEMISTRY  
LOKER HYDROCARBON RESEARCH INSTITUTE  
UNIVERSITY OF SOUTHERN CALIFORNIA  
LOS ANGELES, CALIFORNIA 90089-1661

19971003 011

 8/4/97  
LARRY R. DALTON DATE  
PRINCIPAL INVESTIGATOR

 8/5/97  
PHILIP J. STEPHENS DATE  
CHAIRMAN, CHEMISTRY DEPT.

## REVIEW OF OBJECTIVES :

The systematic investigation of the design and synthesis of second order nonlinear optical chromophores, for significantly improved optical nonlinearity and the capability of being adapted to the fabrication of prototype electro-optic devices, is the primary objective of this program. Chromophores must not only exhibit improved optical nonlinearity relative to acentric azobenzene and stilbene chromophores but must also exhibit appropriate solubility in processing solvents, must be amenable to covalent incorporation into polymeric materials, must exhibit chemical stability under a variety of processing conditions including exposure to elevated temperatures and high electric fields, must be capable of being arranged into macroscopic noncentrosymmetric arrangements yielding large second order optical susceptibilities. A second objective is to explore new processing protocols appropriate for utilizing improved chromophores. This includes investigation of a variety of polymer lattice hardening reactions used in conjunction with induction of chromophore order by electric field poling. A third objective is to carry out a preliminary evaluation of new materials for use with reactive ion and photoprocessing of active and passive waveguide structures. A final objective is to develop polymeric materials capable of incorporating large quantities of trivalent rare earth metal ions which can be used to achieve optical amplification in polymeric optical fibers.

## STATUS OF EFFORT:

Development of Improved Chromophores. A large number of chromophores with  $\mu\beta$  values in excess of  $1000 \times 10^{-48}$  esu (i.e., 2 to 10 times that of the widely used standard DANS) have been synthesized. Molecular hyperpolarizabilities have been characterized by EFISH and hyper-Rayleigh scattering (see Dalton, et al., Chemistry of Materials, 7, 1060-1081 (1995) and Dalton, Chemistry & Industry, no. 13, 510-514, 7 July 1997). Thermal properties have been evaluated by TGA. Structural characterization has been evaluated high resolution NMR, UV-Vis, FTIR, Mass Spectroscopy and by Elemental Analysis. A program has recently been set in place to evaluate photochemical and photophysical properties of chromophores at relevant wavelengths. These chromophores have been prepared with reactive functionalities which permit incorporation into various polymer processing protocols and resulting materials have been evaluated under poling and lattice hardening conditions. Macroscopic electro-optic coefficients, measured by ellipsometry, attenuated total reflection and two-slit interference modulation, have been observed in the range 15 to 70 pm/V. The fact that high  $\mu\beta$  chromophores initially (without chromophore derivatization) exhibited optical nonlinearities

(electro-optic coefficient and second harmonic generation coefficient) significantly below the values predicted by  $\mu\beta/(\text{molecular weight})$  scaling has been quantitatively explained. London theory has been extended to treat the competition of chromophore-electric field (acentric ordering) and chromophore-chromophore (acentric disordering or centric ordering) interactions. The shape of chromophores has been explicitly taken into account. Theoretical calculations quantitatively predict the variation of electro-optic coefficients with chromophore loading in polymeric matrices. In particular, electro-optic coefficients are observed to go through a maximum with chromophore loading (number density). Attenuation of acentric order is shown to be most problematic for prolate ellipsoidal chromophores. Chromophores of spherical shape are likely optimal for maximizing optical nonlinearity but theory predicts that oblate ellipsoidal chromophores should also be explored. The effects of electrical conductivity and photoconductivity on poling-induced acentric order has also been quantitatively investigated. In the process of this investigation chromophores have been identified which offer exciting new levels of photoconductivity and novel optical limiting properties. New Processing Methods. The understanding of the role played by chromophore-chromophore electrostatic interactions in influencing both achievable acentric order and lattice hardening and of the roles played by electrical conductivity and photoconductivity has dramatically influenced electric field poling protocols including the role of cladding layers in such protocols. Specifically new poling protocols, including pulsed field poling, have been introduced and have led to improved optical nonlinearity. In the pulsed field poling protocol, a periodic pulsed field of increased strength is applied, in addition to the lower strength steady state poling field, for short periods of time. The pulse periods are sufficiently short to avoid dielectric breakdown of the materials but are sufficient to disrupt chromophore-chromophore interactions. Because chromophore-chromophore interaction strengths vary dramatically with relative orientation and distance, such transient disruptions allow the steady state field-chromophore interaction to successfully compete with the chromophore-chromophore electrostatic interactions and pole the material. A detailed study of poling-induced optical loss has been carried out. Two primary contributors to such loss have been identified and are (1) surface damage (studied by SIMS) from the corona field and (2) migration of chromophores under the influence of the electric field. A detailed study of optical loss due to material heterogeneities arising during lattice hardening reactions has also been carried out. GPC has been used to investigate oligomer growth and distribution during precuring and lattice hardening. Control crosslinking reagent stoichiometry was found to be particularly critical in minimizing optical loss due to processing.

Substantial strides have also been made in the area of fabricating buried channel waveguides. The superiority of electron cyclotron resonance methods to reactive ion etching has been demonstrated. Control of reactive ion processing conditions has been shown to be relevant to reduction of optical losses in both polymeric waveguides and in the transition of light from polymeric to silica waveguides. Optical losses due to wall roughness in buried channel waveguides have been reduced to 0.01 dB/cm which is insignificant. Coupling losses due to mode mismatch at a silica to polymer waveguide junction have been reduced to less than 2 dB by a systematic investigation of tapered transitions. Polymeric Fiber Amplifiers. Rare earth ion incorporation into polymeric waveguides has been achieved exploiting oxygen and nitrogen chelation. Polymer structure modification (e.g., fluorination) has been carried out to reduce optical loss. Polymer chelates have been developed to minimize quenching of luminescence due to interaction between metal centers. Polymer structures have been controlled to permit preparation of fibers by extrusion although optical characterizations to date have largely been carried out on spin cast thin films. Most recently, a promising series of light harvesting dendrimers have been developed.

#### ACCOMPLISHMENTS/NEW FINDINGS :

1. Theoretically and experimentally demonstrated that the high dipole moments and large molecular polarizabilities of new high  $\mu\beta$  (first hyperpolarizability) chromophores lead to critically important electrostatic intermolecular interaction magnitudes which in turn dominate realizable poling efficiency and strongly influence the efficiency of lattice hardening reactions. The current failure of unmodified "high  $\mu\beta$  chromophores" to be successfully translated into macroscopic electro-optic materials appropriate for device fabrication has been quantitatively explained and insight has been gained into routes appropriate for circumventing current limitations. Indeed, modification of chromophores from their current prolate ellipsoidal shapes to spherical and oblate ellipsoidal shapes appear to provide a simple route to optimizing macroscopic optical nonlinearity through more efficient noncentrosymmetric assembly. Macroscopic optical nonlinearities of a number of chromophores has been improved by factors of 2-3. Preliminary evidence has already been obtained indicating that improved lattice hardening can be realized by chromophore modification to inhibit intermolecular aggregation driven by electrostatic interactions.

The work on London theory can be considered to be a major theoretical breakthrough with relevance to a variety of materials problems including liquid crystalline and block copolymer materials.

2. The role of electrical conductivity and photoconductivity influencing realizable noncentrosymmetric order in electric field poling experiments has been elucidated. The excitation spectrum of photoconductivity has been determined for materials exhibiting large photoconductivities. Excitation across the HOMO-LUMO gap is required for photoconductivity (i.e., two photon contributions are negligible) so that electro-optic modulation operation of these materials at the communication wavelengths of 1.3 and 1.5 microns is not problematic. Photoconductivity effects can be avoided by poling in the dark. Electrical conductivity problems due to ionic contamination can be reduced by appropriate purification techniques such as chromophore recrystallization. Note that because of their large polarizability, high  $\pi$  chromophores may form large transfer adducts with ionic species and care must be exercised in disrupting these and removing ionic impurities.

3. The issue of optical loss due to mode mismatch between silica fiber waveguides and active polymeric electro-optic modulator waveguides has been addressed (Proc. SPIE, 3005, 65-76, 1997). with considerable success exploiting both reactive ion etching (RIE) and multi-color photolithography (MCP) techniques. Tapered transitions, which approximate the profile predicted theoretically by Marcatali (J. Lightwave Technol. 3, 386-93, 1991) for zero loss, have been fabricated and tested. Dramatically reduced coupling losses have been observed. Work on multi-color photolithography has been coordinated with RVM Scientific.

4. New "blue-shifted" high  $\beta$  chromophores have been synthesized for application at 980 nm. This work has been carried out in conjunction with Deacon Research/Gemfire Corporation for development of improved flat panel display technology.

5. New electrically conducting cladding materials have been developed which may facilitate the production of electro-optic devices with reduced  $V_p$  values. New photoconducting materials have been developed which may prove of utility for a variety of applications including cladding materials, photorefractive materials, reconfigurable radar, etc.

6. Further refinements have been made in the area of lattice hardening protocols. New classes of heteroaromatic nonlinear optical polymers which exhibit improved thermal stability of poling-induced optical nonlinearity have been synthesized.

7. Materials and processing protocols have been developed facilitating the vertical integration of polymeric buried channel electro-optic waveguides with VLSI semiconductor electronic circuitry. These has been achieved by the USC team of Steier and Dalton with degradation of the performance of either electro-optic or electronic circuitry.

8. Several new spectroscopic characterization techniques, including frequency-agile, multi-dimensional, multi-wave mixing, phase-sensitive-detection nonlinearity spectroscopy and new techniques for measuring electro-optic coefficients, have been developed.

#### PERSONNEL SUPPORTED:

Larry R. Dalton, Principal Investigator, 1 month summer  
Frederick Strohkendl, Postdoctoral Fellow, partial support  
Joyce Laquindanum, Postdoctoral Fellow, partial support  
Jerome Liang, Postdoctoral Fellow, partial support  
Zhixin Yang, Postdoctoral Fellow, partial support  
Mingqian He, Postdoctoral Fellow, partial support  
Joyce Laquindanum, Graduate Research Assistant, partial support  
Jerome Liang, Graduate Research Assistant, partial support  
Fang Wang, Graduate Research Assistant, partial support  
Jingsong Zhu, Graduate Research Assistant, partial support  
Shajing Sun, Graduate Research Assistant, partial support  
Michael Lee, Graduate Research Assistant, partial support  
Darin Files, Graduate Research Assistant, partial support  
Rima Ghosn, Graduate Research Assistant, partial support  
Joe Larson, Graduate Research Assistant, partial support  
Aaron Harper, Graduate Research Assistant, partial support

Note: Mr. Aaron Harper, Graduate Research Assistant worked full time on research pursued under this program although part of his salary support derived from the award of an American Chemical Society Organic Division Fellowship sponsored by Proctor & Gamble Corporation. Mr. Harper is now Assistant Professor of Chemistry at Texas A&M University.

#### F49620-94-1-0201 PUBLICATIONS \_:

1. C. W. Spangler, M. He, E. G. Nickel, J. Laquindanum, L. R. Dalton, N. Tang, and R. W. Hellwarth, "The Design of New Organic Materials With Enhanced Nonlinear Optical Properties," Mol. Cryst. Liq. Cryst. , **240**, 17-23 (1994).
2. F. P. Strohekendl, D. Files, and L. R. Dalton, "Highly Stable Amplification of Femtosecond Pulses," J. Opt. Soc. Amer., **B11**, 742-749 (1994).

3. N. Tang, J. P. Partanen, R. W. Hellwarth, J. Laquindanum, L. R. Dalton, M. Q. He, and C. W. Spangler, "Studies of Optical Nonlinearity in Bis-Thienyl Polyenes," Proc. SPIE , 2285, 186-95 (1994).
4. M. W. Becker, L. S. Sapochak, L. R. Dalton, Y. Shi, W. H. Steier, and A. K. Jen, "Large and Stable Nonlinear Optical Effects for a Polyimide Covalently Incorporating an NLO Chromophore," Chemistry of Materials, 6, 104-6 (1994).
5. J. B. Caldwell, R. W. Cruse, K. J. Drost, V. P. Rao, A. K.-Y. Jen, K. Y. Wong, Y. M. Cai, R. M. Mininni, J. Kenney, E. Binkley, L. R. Dalton, Y. Shi, and W. H. Steier, "Sol-Gel-Derived Thin Films Incorporating an Organic Second-Order NLO Compound With Large  $\beta$ ," Materials Research Society Symposium Proceedings, Vol. 328, Electrical, Optical and Magnetic Properties of Organic Solid State Materials (Materials Research Society, Pittsburgh, 1994) pp. 535-40.
6. A. K.-Y. Jen, V. P. Rao, K. J. Drost, Y. M. Cai, R. M. Mininni, J. T. Kenney, E. S. Binkley, L. R. Dalton, and S. R. Marder, "Progress on Heteroaromatic Chromophores in High Temperature Polymers for Electro-optic Applications," Proc. SPIE , 2143, 321-40 (1994).
7. A. K.-Y. Jen, K. J. Drost, Y. Cai, V. P. Rao, and L. R. Dalton, "Thermally Stable Nonlinear Optical Polyimides: Synthesis and Electro-Optic Properties," J. Chem. Soc., Chem. Commun., 965-6 (1994).
8. S. Kalluri, W. H. Steier, Z. Yang, C. Xu, B. Wu, L. R. Dalton, Y. Shi, and J. H. Bechtel, "Enhancement of Electro-Optic Properties and Temperature Stability in Sol-Gel Polymer Thin Films," Proc. SPIE , 2285, 67-75 (1994).
9. Y. Shi, J. H. Bechtel, S. Kalluri, W. H. Steier, C. Xu, B. Wu, and L. R. Dalton, "Measurement of Electro-Optic Coefficient Dispersion in Poled Nonlinear Optical Polymer Thin Films," Proc. SPIE , 2285, 131-40 (1994).
10. A. K.-Y. Jen, K. Drost, V.P. Rao, Y. M. Cai, R. M. Mininni, J. Kenney, E. Binkley, L. R. Dalton, and C. Xu, "Highly Active and Thermally Stable Electro-Optic Polymers," Proc. SPIE , 2285 49-57 (1994).
11. S. Gilmour, R. A. Montgomery, S. R. Marder, L.-T. Cheng, A. K.-Y. Jen, Y. M. Cai, J. W. Perry, and L. R. Dalton, "Synthesis of Diarylthiobarbituric Acid Chromophores With Enhanced Second-Order Optical Nonlinearities and Thermal Stability," Chemistry of Materials , 6, 1603-4 (1994).
12. A. K.-Y. Jen, Y.-J. Liu, Y. Cai, V. P. Rao, and L. R. Dalton, "Design and Synthesis of Thermally Stable Side-Chain Polyimides for Second-Order Nonlinear Optical Applications," J. Chem. Soc., Chem. Commun., 2711-12 (1994).
13. Z. Yang, C. Xu, B. Wu, L. R. Dalton, S. Kalluri, W. H. Steier, Y. Shi, and J. H. Bechtel, "Anchoring Both Ends of Chromophores into Sol-Gel Networks for Large and Stable Optical Nonlinearities," Chemistry of Materials, 6, 1899-901 (1994).



14. S.Kalluri, Y. Shi, W. H. Steier, Z. Yang, C. Xu, and L. R. Dalton, "Improved Poling and Thermal Stability of Sol-Gel Nonlinear Optical Polymers," Appl. Phys. Lett., **65**, 2651-3 (1994).
15. B. Wu, C. Xu, L. R. Dalton, S. Kalluri, Y. Shi, and W. H. Steier, "Second-Order Nonlinear Optical Polymers With Different Chromophore Arrangements," Materials Research Society Symposium Proceedings, Vol. 328, Electrical, Optical and Magnetic Properties of Organic Solid State Materials (Materials Research Society, Pittsburgh, 1994) pp. 529-34.
16. C. Xu, B. Wu, L. R. Dalton, Y. Shi, P. M. Ranon, S. Kalluri, and W. H. Steier, "Realization of Large, Stable Second Order Optical Nonlinearities Through Double-End Crosslinkable Chromophores," Materials Research Society Symposium Proceedings, Vol. 328, Electrical, Optical and Magnetic Properties of Organic Solid State Materials (Materials Research Society, Pittsburgh, 1994) pp. 461-6.
17. C. W. Spangler, M. Q. He, J. Laquindanum, L. R. Dalton, N. Tang, J. Partanen, and R. W. Hellwarth, "Bipolaron Formation and Nonlinear Optical Properties in Bis-Thienyl Polyenes," Materials Research Society Symposium Proceedings, Vol. 328, Electrical, Optical and Magnetic Properties of Organic Solid State Materials (Materials Research Society, Pittsburgh, 1994) pp. 655-60.
18. A. F. Garito, A. K-Y. Jen, C. Y-C. Lee, and L. R. Dalton, Eds, Materials Research Society Symposium Proceedings, Vol. 328, Electrical, Optical and Magnetic Properties of Organic Solid State Materials (Materials Research Society, Pittsburgh, 1994) pp. 1-817.
19. C. W. Spangler, M. He, E. Nickel, J. Laquindanum, and L. R. Dalton, N. Tang, and R. W. Hellwarth, "The Design of New Organic Materials With Enhanced Nonlinear Optical Properties," Mol. Cryst. Liq. Cryst., **240**, 17-23 (1994).
20. A. K.-Y. Jen, K. J. Drost, V. P. Rao, Y. Cai, Y.-J. Liu, R. M. Mininni, J. T. Kenney, E. S. Binkley, S. R. Marder, L. R. Dalton, and C. Xu, "The Incorporation of Highly Active and Thermally Stable Heteroaromatic Chromophores into High Temperature Polyimides For E-O Applications," Polymer Preprints, **35**, 130-1 (1994).
21. L. R. Dalton, B. Wu, A. Harper, R. Ghosn, Y. Ra, Z. Liang, R. Montgomery, S. Kalluri, Y. Shi, W. H. Steier, A. K.-Y. Jen, "Techniques of Ultrastructure and Chromophore Synthesis Relevant to the Fabrication of High Frequency Electro-Optic Modulators," Polymer Preprints, **35**, 128-9 (1994); Polymers for Second-Order Nonlinear Optics, Chap. 12, ACS Symposium Series 601 (G. A. Lindsay and K. D. Singer, eds) Amer. Chem. Soc., Washington, DC, 1995, pp. 158-171.
22. M. Ziari, W. H. Steier, L. R. Dalton, Y. Shi, W. Wang, D. Chen, and H. R. Fetterman, "Electrooptic Polymer Waveguide Fabrication," Polymer Preprints, **35**, 227 (1994).

23. F. P. Strohekendl, D. Files, and L. R. Dalton, "Highly Stable Amplification of Femtosecond Pulses," J. Opt. Soc. Amer., **B11**, 742-749 (1994).
24. F. P. Strohekendl, R. J. Larsen, L. R. Dalton, and R. W. Hellwarth, "Nonlinear Optical Properties of a C60 Film Between 740 nm and 880 nm", Proc. SPIE, **2285**, 186-195 (1994).
25. M. Ziari, S. Kalluri, S. Garner, W. H. Steier, Z. Liang, L. R. Dalton, and Y. Shi, "Novel Electro-Optic Measurement Technique for Coplanar Electrode-Poled Polymers," Proc. SPIE , **2527**, 218-27 (1995).
26. S. Garner, S. Kalluri, M. Ziari, W. H. Steier, Y. Shi, Z. Liang, and L. R. Dalton, "A Two Slit Electrooptic Coefficient Measurement Technique and Efficient In-Plane Poling of Polymer Thin Films," Opt. Soc. Amer. Tech. Digest. Ser. , **21**, 383-5 (1995).
27. F. P. Strohekendl, R. J. Larsen, T. J. Axenson, L. R. Dalton, R. W. Hellwarth, H. W. Sarkas, and Z. H. Kafafi, "Nonlinear Optical Properties of a C<sub>70</sub> Film Between 740 and 880 nm", Proc. SPIE, **2530**, 165-74 (1995).
28. L. R. Dalton, C. Xu, A. W. Harper, R. Ghosn, B. Wu, Z. Liang, R. Montgomery, and A. K.-Y. Jen, "Development and Application of Organic Electro-Optic Modulators," Nonlinear Optics , **10**, 383-407 (1995).
29. C. W. Spangler, M. He, P.-K. Liu, E. Nickel, J. Laquindanum, and L. R. Dalton, "The Design of New Organic Materials With Enhanced Nonlinear Optical Properties: Incorporation of Bipolaronic Charge Transfer States," Nonlinear Optics , **10**, 147-152 (1995).
30. L. R. Dalton, A. W. Harper, B. Wu, R. Ghosn, J. Laquindanum, Z. Liang, A. Hubbel, and C. Xu "Polymeric Electro-Optic Modulators: Materials Synthesis and Processing," Advanced Materials , **7**, 519-40 (1995).
31. H. W. Oviatt, Jr., K. J. Shea, S. Kalluri, Y. Shi, W. H. Steier, and L. R. Dalton, "Applications of Organic Bridged Polysilsesquioxane Xerogels to Nonlinear Optical Materials by the Sol-Gel Method," Chemistry of Materials , **7**, 493-8 (1995).
32. Z. Liang, L. R. Dalton, S. M. Garner, S. Kalluri, A. Chen, and W. H. Steier, "Crosslinkable Polyimide for Second-Order Optical Nonlinearities," Chemistry of Materials , **7**, 941-4 (1995).
33. L. R. Dalton, A. W. Harper, R. Ghosn, W. H. Steier, M. Ziari, H. Fetterman, Y. Shi, R. Mustacich, A. K.-Y. Jen, and K. J. Shea, "Synthesis and Processing of Improved Second Order Nonlinear Optical Materials for Applications in Photonics," Chemistry of Materials , **7**, 1060-81 (1995).
34. L. R. Dalton, A. W. Harper, J. Zhu, R. Salovey, J. Wu, and U. Efron, "Ultrastructure Synthesis of Special Architectures for Photonic Applications: High Frequency Electro-Optic Modulators and High Density Optical Memories," Proc. SPIE , **2528**, 106-15 (1995).

35. S. Kalluri, A. Chen, V. Chuyanov, M. Ziari, W. H. Steier, and L. R. Dalton, "Integration of Polymer Electrooptic Devices on Non-Planar Silicon Integrated Circuits," Proc. SPIE , 2527, 375-83 (1995).
36. A. W. Harper, A. Hubbel, J. Laquindanum, Y. Ra, and L. R. Dalton, "Synthesis and Processing Relevant to Systems Integration of Nonlinear Optical Materials," in Polymers and Other Advanced Materials: Emerging Technologies and Business Opportunities, eds., P. N. Prasad, J. E. Mark, and J. J. Fai (Plenum, New York, 1995) pp. 503-10.
37. L. R. Dalton, A. W. Harper, Z. Liang, J. Zhu, U. Efron, C.-S. Wu, and A. Au, "Polymeric Thin Films for Electro-Optic Modulator and High Density Optical Memory Applications," Materials Research Society Symposium Proceedings, Vol. 392, Thin Films for Integrated Optics Applications (Materials Research Society, Pittsburgh, 1995) p. 43-51.
38. A. K.-Y. Jen, T.-A. Chen, V. P. Rao, Y.-M. Cai, Y.-J. Liu, K. J. Drost, R. M. Mininni, L. R. Dalton, P. Bedworth, and S. R. Marder, "Highly Active and Thermally-Stable Chromophores and Polymers for Electro-Optic Applications," Materials Research Society Symposium Proceedings, Vol. 392, Thin Films for Integrated Optics Applications (Materials Research Society, Pittsburgh, 1995) p. 33-41.
39. L. R. Dalton, "Nonlinear Optical Materials," Kirk-Othmer Encyclopedia of Chemical Technology, 4th Ed., Vol. 17, (John Wiley & Sons, New York, 1995), pp 288-302.
40. Z. Liang, L. R. Dalton, S. M. Garner, S. Kalluri, A. Chen and W. H. Steier, "A Heterocyclic Polymer With Thermally Stable Second-Order Optical Nonlinearity," Chemistry of Materials , 7, 1756-8 (1995).
41. L. R. Dalton and A. W. Harper, "Photoactive Organic Materials for Electro-Optic Modulator and High Density Optical Memory Applications," in Photoactive Organic Materials: Science and Application, NATO ASI Series E: Applied Sciences, ed. F. Kajzar, V. M. Agranovich, and C. Y.-C. Lee (Kluwer Academic Publishers, Dordrecht, 1995) pp. 183-198.
42. S. Kalluri, A. Chen, M. Ziari, W. H. Steier, Z. Liang, L. R. Dalton, D. Chen, B. Jalali, and H. R. Fetterman, "Vertical Integration of Polymer Electro-Optic Devices on Electronic Circuits," Opt. Soc. Amer. Tech. Digest. Ser. , 21, 317-20 (1995).
43. A. K.-Y. Jen, V. P. Rao, T.-A. Chen, Y. Cai, K. J. Drost, Y.-J. Liu, J. T. Kenney, R. M. Mininni, P. V. Bedworth, S. R. Marder, and L. R. Dalton, "High Performance Chromophores and Polymers for E-O Applications," Opt. Soc. Amer. Tech. Digest. Ser. , 21, 251-4 (1995).
44. W. Wang, D. Chen, H. R. Fetterman, W. H. Steier, L. R. Dalton, P. M. D. Chow, "Optical Heterodyne Detection of 60 GHz Electro-Optic Modulation From Polymer Waveguide Modulators," Appl. Phys. Lett., 67, 1806-8 (1995).

45. N. Tang, R. W. Hellwarth, J. P. Partanen, S. Sun, and L. R. Dalton, "Optical Limiting in Protonic Doped Bis-Benzothiazole," Mat. Res. Soc. Symp. Proc., **374**, 225-40 (1995).
46. L. R. Dalton, "High Frequency Electro-Optic Modulation and Integration of Photonic and VLSI Electronic Circuitry Demonstrated," Photonics Science News, **1**, 7-9 (1995).
47. A. W. Harper, L. R. Dalton, and A. K.-Y. Jen, "Fabrication of Electro-Optic Modulators from Hardened Plastics," Society of Plastics Engineers Annual Technical Meeting, ANTEC Proceedings 96, Society of Plastics Engineers, Indianapolis, 1996, pp. 1526-9.
48. S. Kalluri, M. Ziari, A. Chen, V. Chuyanov, W. H. Steier, D. Chen, B. Jalali, H. R. Fetterman, and L. R. Dalton, "Monolithic Integration of Waveguide Polymer Electrooptic Modulators on VLSI Circuitry," IEEE Photonics Technology Letters, **8**, 644-6 (1996).
49. S. Kalluri, S. Garner, M. Ziari, W. H. Steier, and L. R. Dalton, "Simple two-slit interference electrooptic coefficients measurement technique and efficient coplanar electrode poling of polymer thin films," Appl. Phys. Lett., **69**, 275-7 (1996).
50. L. R. Dalton, A. W. Harper, and S. J. Sun, "Ultrastructure Synthesis and Nonlinear Spectroscopy of Photonic Materials," Mol. Cryst. Liq. Cryst., **283**, 119-23 (1996).
51. S. J. Sun, A. W. Harper, C. Zhang, L. R. Dalton, S. M. Garner, A. Chen, A. Yacoubian, and W. H. Steier, "Synthesis and Characterization of 1,3-Bis(Dicyanomethylene)indane (BDMI) Derived Second Order NLO Materials," Materials Research Society Symposium Proceedings, Vol. 413, Electrical, Optical and Magnetic Properties of Organic Solid State Materials (Materials Research Society, Pittsburgh, 1996) 263-8.
52. L. R. Dalton, "Polymers for Electro-Optic Modulator Waveguides," in Electrical and Optical Polymer Systems: Fundamentals, Methods, and Applications, eds. D. L. Wise, T. M. Cooper, J. D. Gresser, D. J. Trantolo, and G. E. Wnek, (World Scientific, Singapore, 1996).
53. Z. Liang, Z. Yang, S. Sun, B. Wu, L. R. Dalton, S. M. Garner, S. Kalluri, A. Chen, and W. H. Steier, "Processible and Thermally Stable Heterocyclic Polymers for Second-Order Nonlinear Optical Studies," Chemistry of Materials, **8**, 2681-5 (1996).
54. S. Sun, C. Zhang, L. R. Dalton, S. M. Garner, A. Chen, and W. H. Steier, "1,3-Bis(Dicyanomethylene)indane Based Second Order NLO Materials," Chemistry of Materials, **8**, 2539-41 (1996).
55. A. Chen, K. Kaviani, A. Remple, S. Kalluri, W. H. Steier, Y. Shi, Z. Liang, and L. R. Dalton, "Optimized Oxygen Plasma Etching of Polyurethane Based Electrooptic Polymers for Low Loss Waveguide Fabrication," Journal of the Electrochemical Society, **143**, 3648-51 (1996).

56. L. R. Dalton, "Polymeric Electro-Optic Modulators," Chemistry & Industry, No. 13, 510-4 (1997).
57. Y. Shi, W. Wang, J. H. Bechtel, A. Chen, S. Garner, S. Kalluri, W. H. Steier, D. Chen, H. R. Fetterman, L. R. Dalton, L. Yu, "Fabrication and Characterization of High-Speed Polyurethane-Disperse Red 19 Integrated Electro-Optic Modulators for Analog System Applications," IEEE Journal of Selected Topics in Quantum Electronics , 2, 289-99 (1996).
58. L. R. Dalton, A. W. Harper, and B. H. Robinson, "The Role of London Forces in Defining Noncentrosymmetric Order of High Dipole Moment-High Hyperpolarizability Chromophores in Electrically Poled Polymeric Thin Films," Proc. Natl. Acad. Sci. USA , 94, 4842-4847 (1997).
59. L. R. Dalton, A. W. Harper, S. Sun, W. H. Steier, R. V. Mustacich, and A. K. Y. Jen, "Charge Transfer Interactions in Polymers and the Fabrication of High Frequency Electro-Optic Modulators," Macromol. Symp., 116, 135-42 (1997).
60. D. Chen, H. R. Fetterman, A. Chen, W. H. Steier, L. R. Dalton, W. Wang, and Y. Shi, "High-Bandwidth Polymer Modulators," Proc. SPIE, 3007, 314-17 (1997).
61. C. Koeppen, S. Yamada, G. Jiang, A. F. Garito, and L. R. Dalton, "Rare-Earth Organic-Complexes for Amplification in Polymer Optical Fibers and Wave-Guides," J. Opt. Soc. Amer. B., 14, 155-62 (1977).
62. S. S. Sun, C. Zhang, Z. Yang, L. R. Dalton, S. M. Garner, A. Chen, and W. H. Steier, "Synthesis and Characterization of 1,3Bis(dicyanomethylidene)-indane (BDMI) Based Nonlinear Optical Polymers," Macromolecules, submitted.
63. D. Chen, H. R. Fetterman, A. Chen, W. H. Steier, L. R. Dalton, W. Weng, and Y. Shi, "Demonstration of 110 GHz Electro-Optic Polymer Modulators," Appl. Phys. Lett. , submitted.
64. A. Chen, V. Chuyanov, F. I. Marti-Carrera, S. Garner, W. H. Steier, J. Chen, S. Sun, and L. R. Dalton, "Integrated Polymer Waveguide Mode Size Transformer with a Vertical Taper for Improved Fiber Coupling," Optoelectronic Interconnects and Packaging IV, eds., R. P. Chen and P. S. Guilfoyle, Proc. SPIE , 3005, 65-76 (1997).
65. L. R. Dalton, A. W. Harper, J. Chen, S. Mao, S. Sun, and M. He, "Polymeric Electro-Optic Modulators: From Chromophore Design to Integration with Semiconductor VLSI Electronics and Silica Fiber Optics," Ind. Eng. Chem. Res. , in press (1998).
66. S. S. H. Mao, Y. Ra, L. Guo, C. Zhang, L. R. Dalton, A. Chen, S. Garner, and W. H. Steier, "Progress Towards Device-Quality Second-Order Nonlinear Optical Materials: 1. Influence of Composition and Processing Conditions on Nonlinearity, Temporal Stability and Optical Loss," Chemistry of Materials , 510-14 (1997).

67. L. R. Dalton, A. W. Harper, J. Chen, S. Sun, and S. Mao, S. Garner, A. Chen, and W. H. Steier, "The Role of Intermolecular Interactions in Fabricating Hardened Electro-Optic Materials," Proc. SPIE, CR68, 313-21 (1997).
68. A. W. Harper, S. Sun, L. R. Dalton, S. M. Garner, A. Chen, S. Kalluri, W. H. Steier, and B. H. Robinson, "Translating Microscopic Optical Nonlinearity to Macroscopic Optical Nonlinearity: The Role of Chromophore-Chromophore Electrostatic Interactions," J. Opt. Soc. Amer. B, In press; Opt. Soc. Amer. Tech. Digest, Solid State Lasers: Materials and Applications, 82-4 (1997).
69. A. K. Y. Jen, T. A. Chen, Y. Zhang, Y. J. Liu, X. Q. Zhang, J. T. Kenney, and L. R. Dalton, "Recent Developments of High Performance Electro-Optic Materials for Device Applications," J. Opt. Soc. Amer. B, in press.
70. A. W. Harper and L. R. Dalton, "Polymeric Electro-Optic Modulators: Generation of Acentric Chromophore Lattices and Processing of Buried Channel Waveguides," ANTEC Proceedings 97, 919, 1382-5 (1997).
71. F. Wang, A. W. Harper, M. He, A. Ren, L. R. Dalton, S. M. Garner, A. Yacoubian, A. Chen, and W. H. Steier, "Design and Synthesis of a Perfluoroalkyldicyanovinyl-Based NLO Material for Electro-Optic Applications," Organic Thin Films, ACS Symposium Series 000 (C. W. Frank, ed.) Amer. Chem. Soc., Washington, DC, 1997, in press.
72. M. He, J. Zhu, A. W. Harper, S. S. Sun, L. R. Dalton, S. M. Garner, and W. H. Steier, "Progress Towards the Transition of Large Microscopic Nonlinearities to Large Macroscopic Nonlinearities for High- $\mu\beta$  Materials," Organic Thin Films, ACS Symposium Series 000 (C. W. Frank, ed.) Amer. Chem. Soc., Washington, DC, 1997, in press.
73. S. S. H. Mao, Y. S. Ra, M. He, J. Zhu, C. Zhang, L. R. Dalton, S. Garner, and W. H. Steier, "Progress Toward Device-Quality Second-Order NLO Materials. 2. Enhancement of Electric Poling Efficiency and Temporal Stability by Modification of Isoxazolone Based High  $\mu\beta$  Chromophores," Chemistry of Materials, submitted.
74. S. S. H. Mao, Y. S. Ra, L. Guo, C. Zhang, L. R. Dalton, A. Chen, and W. H. Steier, "Progress Toward Device-Quality Second-Order NLO Materials. 3. Deteriorative Effect of Chromophore Aggregation on Optical Loss," Chemistry of Materials, submitted.
75. Y. S. Ra, S. S. H. Mao, B. Wu, L. Guo, L. R. Dalton, A. Chen, and W. H. Steier, "Thermoset Second-Order NLO Materials From a Trifunctionalized Chromophore," Polym. Prepr., 38, 86-8 (1997).
76. A. Chen, V. Chuyanov, H. Zhang, S. Garner, W. H. Steier, J. Chen, J. Zhu, M. He, S. S. H. Mao, and L. R. Dalton, "Demonstration of the Full Potential of Second Order Nonlinear Optic Polymers for Electrooptic Modulation Using a

High  $\mu\beta$  Chromophore and a Constant Bias Field," Appl. Phys. Lett., submitted.

77. J. Chen, J. Zhu, M. He, L. R. Dalton, S. Garner, A. Chen, W. H. Steier, "High E-O Coefficient Polymers Based on a Chromophore Containing Isophorone Moiety for Second-Order Nonlinear Optics," Materials Research Society Symposium Proceedings, Vol. 000, Electrical, Optical and Magnetic Properties of Organic Solid State Materials (Materials Research Society, Pittsburgh, 1998) in press.

78. A. W. Harper, J. Zhu, M. He, L. R. Dalton, S. M. Garner, and W. H. Steier, "Characterization and Circumventing Electrostatic Intermolecular Interactions in Highly Electro-Optic Polymers," Materials Research Society Symposium Proceedings, Vol. 000, Electrical, Optical and Magnetic Properties of Organic Solid State Materials (Materials Research Society, Pittsburgh, 1998) in press.

79. S. Thayumanavand, K. Staub, J. Mendez, A. K. Y. Jen, L. R. Dalton, S. Ermer, B. Kippelen, N. Peyghambarian, and S. R. Marder, "Design of Second Order NLO Chromophores for Electro-Optic Applications," Materials Research Society Symposium Proceedings, Vol. 000, Electrical, Optical and Magnetic Properties of Organic Solid State Materials (Materials Research Society, Pittsburgh, 1998) in press.

#### INTERACTIONS/TRANSITIONS :

##### INVITED LECTURES:

1. Third International Conference on Frontiers of Polymers and Advanced Materials, Kuala Lumpur
2. 28th Organosilicon Symposium, Gainesville, Florida
3. 1995 ACS/PMSE Symposium on Polymeric Organic Materials: Solid State Properties and Smart Materials, Anaheim, California
4. Materials Research Society Symposium on Thin Films for Integrated Optics Applications, San Francisco, California
5. National Technology Transfer Center, Technology Applications Review, Orlando, Florida
6. NASA Lecturer, Fifty Fourth Frontiers in Chemistry Lecture Series, Cleveland, Ohio
7. NATO Advanced Research Workshop on Photoactive Organic Materials: Science and Applications, Avignon, France
8. SPIE International Symposium on Nonlinear Optical Properties of Organic Materials VIII, San Diego, California
9. SPIE International Symposium of Optical and Photonic Applications of Electroactive and Conducting Polymers, San Diego, California

10. SPIE International Symposium on Fullerenes and Photonics II, San Diego, California
11. Symposium on Optoelectronic Materials and Conjugated Polymers, IV International Conference on Advanced Matierals, Cancun, Mexico
12. 7th International Conference on Unconventional Photoactive Systems, Stanford, California
13. OSA/ACS Organic Thin Films for Photonics Applications, Portland, Oregon
14. International Business Communications Conference on Commercial Applications for Organo Electronic Materials, Mariana del Rey, CA
15. Society of Plastics Engineers (SPE) annual technical meeting ANTEC, Indianapolis, IN
16. American Chemical Society National Meeting, New Orleans, LA
17. American Chemical Society National Meeting, Orlando, FL
18. SPIE International Symposium on Fullerenes and Photonics III, Denver, CO.
19. ACS/OSA Symposium on Organic Thin Films for Photonic Applications, Orlando, Florida
20. International Conference on Nonlinear Optics 3, Marco Island, Florida
21. Fourth International Conference on Frontiers of Polymers and Advanced Materials, Cairo, Egypt
22. Symposium on Dendrimers and Hyperbranched Polymers, Spring American Physical Society National Meeting, Kansas City, Mo.
23. National Meeting, ANTEC, Society of Plastics Engineers, Toronto, Canada
24. AFOSR/ONR Photonic and Electro-Optic Polymer Review, Atlantic Beach, Florida
25. Sino-American Topical Meeting and Exhibit, Solid State Lasers: Materials and Applications, Tianjin, People's Republic of China
26. Gordon Coference on Organic Thin Films, Salve Regina
27. The International Society of Optical Engineering 42nd Annual Meeting, San Diego, CA.

#### INVITED SEMINARS :

Numerous seminars at various industries, government laboratories, and universities including seminars at University of Florida, University of Illinois, University of Washington, NASA Marshall Space Flight Center, University of California at Los Angeles, the Max-Planck-Institut fur Polymerforschung (Mainz FRG) and the Optical Science Center of the University of Arizona.



Presentations were also made before the Board of Gemfire Corporation, senior management of Hughes Research Laboratories, the Board of the Loker Hydrocarbon Research Institute and the Board of Trustees of the University of Southern California, etc.

CONSULTATIVE AND ADVISORY PANEL SERVICE :

1. Bule Ribbon (Final Phase) Panel for the Selection of Presidential Faculty Fellows (National Science Foundation)
2. Consultant, Medical Research Service, Veterans Administration
3. Materials Research Science & Engineering Center Panel, National Science Foundation
4. Panel 15, Office of Energy Efficiency and Renewable Energy Photovoltaics Review, U.S. Department of Energy
5. Advisory Committee, National Institutes of Health Biomedical Technology Centers at the University of Illinois and at Dartmouth University
6. Consultant, Arizona Disease Control Research Commission, State of Arizona
7. Immunobiology Study Section, National Institutes of Health
8. Advisory Committee, The New York Herman F. Mark Institute for Polymers Science and Engineering at the Polytechnic University, NY, NY
9. Editorial Advisory Board, Chemistry of Materials, American Chemical Society
10. Consultant, Princeton Materials Research Center.

INTERACTIONS AND TRANSITIONS :

Research Interactions and Technology Transitions include EniChem/ROI Tech/Lightwave Microsystems Corp. (A. Jen/J. Kenney), Cal Tech/JPL (S. Marder and J. Perry), Hughes Research Laboratory (U. Efron), TACAN/Integrated Photonics Technology, Ipitex (Y. Shi), AdTech (S. Sinha), Deacon Research/Gemfire (W. Bischel), RVM Scientific (R. Mustacich), IBM (D. Burland), Physical Optics Corporation (G. Savant), and Thermax Systems, Inc. (Bruce Sangster), Radiant Research, Inc (B. Davies and R. Chen).

NLO active polymeric films were provided to TACAN/Ipitex, RVM Scientific, Deacon Research/Gemfire and Physical Optics Corporation to permit these organizations to pursue evaluation of these materials for phototype device development. TACAN and POC are interested in low frequency, low cost modulator fabrication. TACAN is interested in evaluating the long term, in-field performance of polymeric electro-optic modulators. RVM Scientific is interested in using new photolithographic

techniques to fabricate low loss waveguides and low loss transitions from polymer waveguides to silica fiber transmission lines. Deacon Research is interested in fabricating full color, flat panel displays from polymeric electro-optic modulators.

Photoactive chromophores were transitioned to Hughes Research Laboratory for use in development of high density optical memories.

Thermax Systems, Inc. is interested in using photoactive chromophores in cooling applications.

Discussions have been held with Exxon, Allied Signal and Audemars Corporations and with NASA Marschall Space Flight Center who have expressed interest in collaborating and participating in technology transfer.

#### INVENTIONS:

None

#### HONORS/AWARDS

1. The 1996 Richard C. Tolman of the American Chemical Society (April 23, 1997)
2. Paul C. Cross Endowed Lectureship in Chemistry, University of Washington, Seattle, WA, May 29, 1996
3. NASA Lecuturer, 54th Frontiers of Chemistry Lecture Series, Case Western Reserve University, Cleveland, OH, April 27, 1995.
4. Harold and Lillian Moulton Distinguished Professorship of Chemistry (Endowed Chair), University of Southern California
5. Scientific Co-Director of the Loker Hydrocarbon Research Institute, University of Southern California
6. Nominated for the National Academy of Science
7. Nominated for the Chemistry of Materials Award of the American Chemical Society

The research has been featured in the news articles in the following publications: The Baltimore Sun newspaper, Chemical & Engineering News, Research & Development Magazine, Laser World Focus, Business Week, Science, Wired Magazine, Photonics Spectra, Chemistry & Industry, Polymer Science News, Photonics Science News, Ind. Eng. Chem. Res., etc. A television episode of "Strange Universe" will focus on the research; the filming was completed recently at the Loker Hydrocarbon Research Institute. The research has been featured on two occasions on local radio broadcasts.

Note: Mr. Aaron Harper was the first receiptent of the American Chemical Society Organic Division Fellowship. Mr. Harper is now an Assistant Professor of Chemistry at Texas A&M University.